

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C01B 3/00	A1	(11) International Publication Number: WO 97/43206 (43) International Publication Date: 20 November 1997 (20.11.97)
<p>(21) International Application Number: PCT/CA97/00324</p> <p>(22) International Filing Date: 13 May 1997 (13.05.97)</p> <p>(30) Priority Data: 08/645,352 13 May 1996 (13.05.96) US</p> <p>(71) Applicants: HYDRO-QUEBEC [CA/CA]; 75 West René-Lévesque, Montreal, Quebec H2Z 1A4 (CA). MCGILL UNIVERSITY [CA/CA]; 845 West Sherbrooke, Montreal, Quebec H3A 2T5 (CA).</p> <p>(72) Inventors: ZALUSKA, Alicja; 7242 Hamilton, Montreal, Quebec H4E 3E1 (CA). ZALUSKI, Leszek; 7242 Hamilton, Montreal, Quebec H4E 3E1 (CA). STROM-OLSEN, John; 443 Lansdowne Avenue, Westmount, Quebec H3T 2V4 (CA). SCHULZ, Robert; 68 Bel Horizon, Sainte-Julie, Quebec J0L 2S0 (CA).</p> <p>(74) Agent: ORLHAC, Thierry; Robic, 55 St. Jacques, Montreal, Quebec H2Y 3X2 (CA).</p>		<p>(81) Designated States: CA, CN, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: METHOD FOR INDUCING HYDROGEN DESORPTION FROM A METAL HYDRIDE</p> <p>(57) Abstract</p> <p>Disclosed is a method for inducing desorption of hydrogen from a metal hydride by applying thereto sufficient energy to induce hydrogen desorption by endothermic reaction. The energy that is so-applied is non-thermal and selected from the group consisting of mechanical energy, ultrasonic energy, microwave energy, electric energy, chemical energy and radiation energy.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WO 97/43206

PCT/CA97/00324

1

**METHOD FOR INDUCING HYDROGEN DESORPTION
FROM A METAL HYDRIDE**

BACKGROUND OF THE INVENTION

5

a) Field of the invention

The present invention relates to a method for inducing desorption of hydrogen from a metal hydride containing the same, in which a non-thermal energy source is used to induce such desorption.

10

b) Brief description of the prior art

Metal hydrides are potentially ideal candidates for hydrogen storage and transportation. As hydrogen carriers, they provide high hydrogen storage capacities (up to for example 7.6 wt. % in Mg_2H_2) and full safety. The safety is provided by endothermic reaction of hydrogen release, which excludes spontaneous (explosive) or uncontrolled reaction.

Metal hydrides are advantageous in that they can be handled and stored at ambient temperature without any atmosphere or pressure requirements. Such makes them economically favorable by elimination of cryogenic equipment necessary to use with liquid hydrogen or activated charcoal.

Metal hydrides are also very stable. Such is advantageous from a safety and economical point of view. However, because of their stability, most of the metal hydrides require elevated temperatures to initiate desorption.

Examples of metal hydrides having a high stability are MgH_2 or Mg_2NiH_4 . They exhibit excellent hydrogen storage potential - with large hydrogen storage capacity (7.65 wt. % for MgH_2 or 3.6 wt. % for Mg_2NiH_4), low cost of the material and easy handling. However, desorption of hydrogen from these hydrides with reasonable kinetics requires heating to high temperatures: 350 - 400°C for MgH_2 and 330 - 360°C for Mg_2NiH_4 .

For many applications, heating to such temperatures is disadvantageous. Indeed, it increases technical problems of hydrogen recovery and reduces effectiveness of the devices.

WO 97/43206

PCT/CA97/00324

2

To solve this problem, it has already been suggested to reduce the stability of high temperature metal hydrides. Such may be obtained by alloying the metal hydrides with other elements. However, stability reduction occurs at the expense of the total hydrogen capacity.

5

OBJECT AND SUMMARY OF THE INVENTION

The object of the present invention is to provide an alternative approach to facilitate desorption of hydrogen from a high temperature metal
10 hydride.

More particularly, the invention is based on the discovery that, instead of using a conventional heat source, use can be made of a non-thermal energy source to initiate hydrogen release and thus to induce hydrogen desorption.

15 The expression "non-thermal energy sources" as used in the present specification and claims does not necessary exclude energy sources where heat is produced, like electric energy where heat is produced by Joule effect. As a matter of fact, this expression is exclusively used to exclude "conventional" heat sources such as gas or oil burners where heat is produced
20 and transferred mainly by convection to the metal hydrides.

Examples of non-thermal energy sources that can be used in accordance with the invention for releasing hydrogen from metal hydrides include:

- 25 1. microwave energy,
2. electric energy,
3. chemical energy,
4. mechanical energy,
5. ultrasonic energy, and
6. radiation.

30 Thus, the present invention as broadly claimed hereinafter, is directed to a method for inducing desorption of hydrogen from a metal hydride by applying thereto sufficient energy to induce hydrogen desorption by endothermic reaction, wherein the energy that is so applied is non-thermal and

WO 97/43206

PCT/CA97/00324

3

selected from the group consisting of mechanical energy, ultrasonic energy, microwave energy, electric energy, chemical energy and radiation energy.

The invention and its advantages will be better understood upon reading the following, non-restrictive description and examples.

5

DETAILED DESCRIPTION OF THE INVENTION

As aforesaid, the invention is based on the discovery that instead of using a heat source as it has been done so far, use can be made of a non-thermal energy source to induce hydrogen desorption from a metal hydride.

Thus, instead of using heat energy to raise the temperature of the environment of the hydride in order to induce the endothermal reaction of desorption of hydrogen from the same, energy is supplied to the hydride either intrinsically and on a local scale.

15 This energy may be applied directly on the metal hydride, or indirectly on an energy-carrier medium located in the proximity of the hydride.

Depending on the selected energy source, there are two ways of applying the energy to the hydride. The first one consists of inducing the desorption process by intrinsically heating the hydride (or the heating medium).
20 Such is achieved when use is made of microwave energy, chemical energy where heat is generated by a chemical reaction, or electric energy where heat is generated by Joule effect. The other way consists of introducing and accumulating energy in the hydride to cause desorption, for example by mechanical energy (in the form of strain and defects) or by radiation energy.
25 In this particular case, desorption is much easier than when the hydride is activated by heat. Moreover, after mechanical or radiation pretreatment, the desorption temperature is significantly reduced.

The way each of the above mentioned, alternative energy sources can be used will now be explained in greater details.

30

WO 97/43206

4

PCT/CA97/00324

1. Microwave energy

In accordance with the invention, microwave energy can be directly applied onto the hydride or on a suitable medium intermixed with the hydride to allow for local release of hydrogen, without heating the whole system and under controlled conditions. This method provides high efficiency of desorption, which occurs at temperatures lower than those achieved under conventional heating conditions, due to an excitation by the microwaves of the bonds in the hydride.

The desorption may be conducted in two ways. The first one of these ways consists of using microwaves to achieve release of the whole hydrogen content. The other way consists in using microwave treatment just to initialize the desorption process which then can be continued by conventional heating at lower temperatures and in a much easier way than when heated in a conventional way.

2. Electric energy

Another method to induce hydrogen desorption consists in heating the hydride by means of an electric resistance embedded into the same. The energy of the current flowing into the resistance is converted into heat by Joule effect. The amount of heat created locally by the current flow is particularly high in the case of compressed powder material, with hot spots on the current paths between powder particles, where resistivity is very high. In extreme cases, powder welding may occur at the hot spots. Therefore, the current parameters should be adjusted properly to avoid sintering. Depending on the particular conditions of the process, the hydrides may be heated directly, or with the use of the current carrier medium.

3. Chemical energy

Another method to reduce hydrogen desorption consists of mixing fine particles of the metal hydrides with an appropriate amount of a substance that decomposes spontaneously under exothermic conditions at

WO 97/43206

5

PCT/CA97/00324

a desirable temperature range (for example 50 - 100°C), or with a mixture of products that exothermically react with each other to produce a large amount of heat.

5

4. Mechanical energy

Another method of inducing hydrogen desorption from a metal hydride consists of applying mechanical energy by ball milling to a powder of the metal hydride (which is the usual form of metal hydride). It is well established that ball milling is capable of generating a sufficient amount of mechanical energy to cause formation of various compounds (nitrides, borides,) or alloys (mechanical alloying). In the present case, ball milling can be used either to decompose the metal hydride and release hydrogen, or to accumulate so much strain and defects in the hydride that further heat-activated desorption is facilitated. Temperature of desorption of metal hydrides treated mechanically may be then reduced by 100 - 200°C, which is of great significance for practical application.

5. Ultrasonic energy

Another method of inducing hydrogen description consists in applying ultrasonic energy to the metal hydride. By using a liquid such as water or alcohol as an energy carrier medium, it is possible to generate shock waves and localized heating by acoustic cavitation, with formation of hot spots reaching a temperature as high as 5000°K (in the case of extremely high-intensity ultrasound sources) over periods of less than 1 microsecond.

Thus, sonochemistry, which is already successfully used for the thermal synthesis of amorphous metals or nano-scaled catalysts from volatile organometallics, may be adapted for hydrogen desorption from metal hydrides. The hydride powder immersed in a liquid medium acting as an energy carrier and subjected to ultrasound of adjusted intensity, decomposes

WO 97/43206

PCT/CA97/00324

6

at hot spots created by acoustic cavitation and releases hydrogen, without significant increase of the total temperature of the system. It provides an easy and efficient hydrogen desorption.

5 6. **Radiation energy**

Desorption of hydrogen from metal hydrides can also be induced by using radiation energy produced by high intensity light sources, ion sources, lasers and the like.

10 The method according to the invention has numerous practical applications. Some of the proposed energy sources, like the microwave and electric energies, do not affect the structure of the metal hydride and the reversibility of the hydrogen absorption/desorption. Thus, it can be used to initiate hydrogen desorption in rechargeable hydrogen storage tank, to start hydrogen-fuelled engine or vehicle. In this connection, reference can be made
15 to U.S. patent application serial No. 08/ filed on January 19, 1996 in the name of the same Applicants, which is hereby incorporated by reference.

Other energy sources like chemical and mechanical energies, affect the structure of metal hydride. In such a case, the method according to the invention may be used for inducing hydrogen desorption in disposable
20 hydrogen storage tanks (for camping units or similar use).

Further energy sources like microwave and radiation energies are rather expensive and need substantial equipments. In such case, the method according to the invention can be used in power systems or units, where a large amount of hydrogen is needed rapidly.

25

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a curve showing the change of X-ray diffraction pattern of a Mg-hydride powder heated at time intervals of 1 minute in a microwave
30 unit (the plain line shows the diffraction before heating, the dotted line after heating); and

WO 97/43206

PCT/CA97/00324

7

Fig. 2 are differential scanning calorimetry (DSC) curves of a Mg-based hydride as prepared (a) and after 2, 7 and 9 minutes of ball milling (curves (b), (c) and (d), respectively).

5

EXAMPLE 1 - microwave energy

A powder of a Mg-based hydride was heated in a microwave unit. Samples were examined after successive heating for the time intervals of 1 minute. X-ray diffraction for this series of samples showed consecutive
10 disappearance of the hydride reflections from the diffraction pattern and increase of the pattern of metal reflections, which is indicative of decomposition of the metal hydride (Fig. 1).

This test also showed that a very short heating time (less than 1 minute) does not release significant amount of hydrogen, but causes a
15 substantial reduction in the desorption temperature, as demonstrated by DSC measurements.

EXAMPLE 2 - chemical energy

A powder of the Mg-based hydride was mixed with a small
20 amount of a powder of lithium aluminum hydride (LiAlH_4). Addition of an appropriate amount of water (moisture) caused a rapid and exothermic reaction according to the following equation:



25

This reaction released a large amount of heat ($109 \pm 4.2 \text{ kJ/molH}_2$), which caused desorption of hydrogen from the Mg-based hydride.

30

EXAMPLE 3 - mechanical energy

A Mg-based hydride was submitted to a mechanical pretreatment before desorption. In the as-prepared state, it exhibited a high temperature of desorption equal to about 400°C , when measured by differential scanning

WO 97/43206

PCT/CA97/00324

8

calorimetry (DSC) at continuous heating with heating rate of 40 K/min (see Fig. 2, curve a). Ball milling in a SPEX[®] mill caused a decrease in the desorption temperature due to an accumulation of mechanical energy in the form of strain and defects. Curves b, c and d represent effects of ball milling of the hydride for 2, 7, 9 min., respectively. The temperature of desorption was decreased by 200°C in the last case (see Fig. 2).

EXAMPLE 4 - ultrasonic energy

10 A powder of Mg-based hydride was placed in an ultrasonic water bath. The container with the hydride was connected by a capillary tube to the water bath outside the ultrasonic device. During ultrasonic treatment, large gas bubbles appeared in the water bath at the end of the capillary indicating hydrogen release from the hydride. Both X-ray diffraction and DSC
15 measurements of the hydride after ultrasonic treatment showed that desorption of hydrogen occurred.

WO 97/43206

9

PCT/CA97/00324

WHAT IS CLAIMED IS

1. A method for inducing desorption of hydrogen from a
5 metal hydride by applying thereto sufficient energy to induce hydrogen
desorption by endothermic reaction, wherein the energy that is so applied is
non-thermal and selected from the group consisting of mechanical energy,
ultrasonic energy, microwave energy, electric energy, chemical energy and
radiation energy.
10
2. The method of claim 1, wherein the selected energy is
applied directly on the metal hydride.
3. The method of claim 1, wherein the selected energy is
15 applied indirectly on an energy carrier medium adjacent to the metal hydride.
4. The method of claim 1, wherein the selected energy is
microwave energy.
- 20 5. The method of claim 4, wherein the microwave energy is
used exclusively to induce the hydrogen desorption, which is completed by
thermal heating.
6. The method of claim 4, wherein the microwave energy is
25 the only source of energy used to achieve the requested desorption.
7. The method of claim 1, wherein the selected energy is
electric energy.
- 30 8. The method of claim 7, wherein the electric energy is
applied to the metal hydride via an electric resistance which is embedded into
said hydride and which acts as a source of heat by Joule effect.

WO 97/43206

PCT/CA97/00324

10

9. The method of claim 8, wherein the electric energy is the only source of energy used to achieve the requested description.

10. The method of claim 1, wherein the selected energy is
5 chemical energy.

11. The method of claim 10, wherein the chemical energy is applied to the metal hydride by incorporating into said metal hydride chemical products that exothermically react with each other and thus produce heat.
10

12. The method of claim 11, wherein the chemical energy is the only source of energy used to achieve the requested desorption.

13. The method of claim 1, wherein the selected energy is
15 mechanical energy which is applied to the metal hydride by subjecting said metal hydride to a high energy mechanical grinding.

14. The method of claim 13, wherein the mechanical energy is used exclusively to induce the hydrogen desorption which is subsequently
20 completed by thermal heating.

15. The method of claim 1, wherein the selected energy is ultrasonic energy.

25 16. The method of claim 15, wherein the ultrasonic energy is the only source of energy used to achieve the requested desorption.

17. The method of claim 16, wherein the metal hydride is immersed into a ultrasonic bath prior to application of the ultrasonic energy.
30

18. The method of claim 1, wherein the selected energy is radiation energy.

WO 97/43206

11

PCT/CA97/00324

19. The method of claim 18, wherein the radiation energy is
5 generated by a source which is selected from the group consisting of high-
intensity light sources, ion sources and lasers and is the only source of energy
used to achieve the requested desorption.

WO 97/43206

PCT/CA97/00324

1/2




FIG. 1

WO 97/43206

PCT/CA97/00324

2 / 2




FIG. 2

INTERNATIONAL SEARCH REPORT

Inter- national Application No
PCT/CA 97/00324

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C01B3/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 1 568 374 A (ATOMIC ENERGY AUTHORITY UK) 29 May 1980 see page 2, line 24 - line 31 ---	1
A	US 4 383 606 A (HUNTER JAMES B) 17 May 1983 see column 4, line 56 - column 5, line 4 ---	1
A	EP 0 088 649 A (IWATANI & CO) 14 September 1983 see page 5, line 17 - line 31 ---	1
A	GB 2 164 637 A (GENERAL ELECTRIC COMPANY) 26 March 1986 see page 3, line 34 - page 4, line 52 -----	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

4 September 1997

Date of mailing of the international search report

30.09.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Clement, J-P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 97/00324

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 1568374 A	29-05-80	NONE	
US 4383606 A	17-05-83	NONE	
EP 0088649 A	14-09-83	JP 1371233 C	25-03-87
		JP 58140301 A	20-08-83
		JP 61037517 B	23-08-86
		JP 1371234 C	25-03-87
		JP 58140302 A	20-08-83
		JP 61037518 B	23-08-86
		CA 1183464 A	05-03-85
		US 4490348 A	25-12-84
GB 2164637 A	26-03-86	DE 3533477 A	17-04-86
		FR 2570689 A	28-03-86
		JP 61111901 A	30-05-86